

MACARONI TABLE		API 10RD										
O.D.	Nominal Weight		Grade	Collapse	Internal Minimum	Joint Strength			BODY YIELD	WALL	I.D.	DRIFT DIAMETER
					PSI							
inch	T&C (lbs/ft)			psi	PE,	lbs			lbs	inch	inch	inch
	NUE	EUE			NUE	NUE	IJ	EUE				
	T&C	T&C			T&C	T&C		T&C				
1"	1.14	1.2	J-55	10560	10360	8740		18300	18300	0.113	0.824	0.73
1"	1.14	1.2	L-80	15370	15070	12720		26600	26600	0.113	0.824	0.73
1"	1.14	1.2	N-80	15370	15070	12720		26600	26600	0.113	0.824	0.73
1 1/16"	1.7	1.8	H-40	7270	7080	10960		19800	19800	0.133	1.049	0.955
1 1/16"	1.7	1.8	J-55	10000	9730	15060	21960	27200	27200	0.133	1.049	0.955
1 1/16"	1.7	1.8	L-80	14550	14160	21910	31940	39500	39500	0.133	1.049	0.955
1 1/16"	1.7	1.8	N-80	14550	14160	21910	31940	39500	39500	0.133	1.049	0.955
1 1/4"	2.3	2.4	H-40	6180	5900	15530	31940	26700	26700	0.14	1.38	1.286
1 1/4"	2.3	2.4	J-55	8490	8120	21360	30500	36800	36800	0.14	1.38	1.286
1 1/4"	2.3	2.4	L-80	12360	11810	31060	44370	53500	53500	0.14	1.38	1.286
1 1/4"	2.3	2.4	N-80	12360	11810	31060	44370	53500	53500	0.14	1.38	1.286
1 1/2"	2.75	2.9	H-40	5640	5340	19100	25824	32000	32000	0.145	1.61	1.516
1 1/2"	2.75	2.9	J-55	7750	7350	26300	36970	44000	44000	0.145	1.61	1.516
1 1/2"	2.75	2.9	L-80	11280	10680	38200	53780	64000	64000	0.145	1.61	1.516
1 1/2"	2.75	2.9	N-80	11280	10680	38200	53780	64000	64000	0.145	1.61	1.516
2 1/16"	3.25		H-40	5590	5290		35700	35700	37400	0.156	1.751	1.657
2 1/16"	3.25		J-55	7690	7280		49070	49100	51400	0.156	1.751	1.657
2 1/16"	3.25		L-80	11180	10590		71370	71400	74800	0.156	1.751	1.657
2 1/16"	3.25		N-80	11180	10590		71370	71400	74800	0.156	1.751	1.657
2 1/16"	3.25		P-110	15680	14560		98050	98100	102800	0.156	1.751	1.657

